

FAÇADE ADHESIVE - SEALANT FS-011

1. Description

Giscosa Façade Adhesive - Sealant FS-011 is a pasty adhesive - sealant ready for use, with unique qualities for horizontal and vertical bonding of EPDM rubber sheeting.

2. Characteristics

- One-sided bonding of EPDM membrane on different substrates, and on its own.
- The bonding assembly is elastic and waterproof.
- When completely dry, the bonding assembly resists temperatures up to 80°C.
- Provided an excellent bond on many materials, such as EPDM membranes, acrylic glass, steel, stone, concrete, aerated concrete, lead, wood, for other substrates connect with Technical Department.
- The minimum processing temperature is 5°C.

3. Application

The maximum open time depends very much on the weather, in general, leaving things uncovered for a maximum of five minutes still produces satisfactory bonding.

The substrates must be clean, free of oil and greases, and dry. Wet substrates or substrates covered with dew must be dried by means of hot air before bonding.

Dirty surfaces and tools may be cleaned with unleaded petrol.

Apply the adhesive sealant in stripes onto the substrate by means of a cartridge gun, then, after a minute, place the rubber membrane onto the adhesive-sealant and press down firmly with a roller.

When bonding vertically, in some cases, it may be necessary, depending on the weight of the membrane, to detach it for a moment after applying the adhesive-sealant and pressing down the membrane, and then place it again and pressing down firmly.

4. Coverage

In accordance with length of works.

5. Properties

Base	Synthetic Rubber
Colour	Black
Solids (%)	78 ± 2

6. Packaging / Storage / Shelf Life

Packaging: 600 ml sausage - 12 units / box

Storage: Store in original unopened containers at temperatures between 15°C and 25°C. Keep the material out of direct sunlight until ready for application.

Shelf Life: Maximum 9 months, when stored in above-mentioned conditions. Verify production date on each roll. Shelf life will be reduced if exposed to higher temperatures.

7. Precautions

- Flammable.
- Avoid open flames or other sources of ignition.
- Do NOT SMOKE when using.
- Refer to the material safety Data Sheet.