

LS 009

1. Description:

LS-009 is a lap sealant that has been designed to seal and protect mechanically the exposed edges of all the joints carried out on site.

It is also used when self-adhesive products of the Giscosa waterproofing system have been cut.

2. Characteristics

- Elasticity.
- Excellent resistance when exposed to the elements.
- Excellent cold, heat and water resistance.
- Very good adhesion to Gisolene waterproofing membranes, metal, wood and cement.
- Does not peel off.

3. Installation

If it has been exposed to temperatures below 15°C, it must be conditioned at room temperature.

The edges and flaps on which it is going to be applied must be clean, smooth and dry.

Wait at least 4 hours after the joint is made until the LS-009 sealant is applied. If the weather seems to be going bad, the sealant must be applied before the work day ends.

LS-009 sealant is applied with a cartridge gun and then a bevelled edge must be cut with the blade that Giscosa supplies. Make sure that the whole joint is covered properly with the LS-009 lap sealant.

Contact the Giscosa Technical Department if you would like any additional information.

4. Coverage

Between 6 and 7 metres long per cartridge.

5. Properties

Base	Butyl
Colour	Black
Solids	80% approx.
Density	1.30 ± 0.05
Surface drying time	15 minutes approx.

6. Presentation/Storage/Expiry

Boxes of twenty-five 310-ml tubes.

The product should be used before 12 months, if the material is stored in the original container, closed tightly, and at temperatures between 15-25°C.

7. Precautions

- Contains flammable solvents
- Keep away from sources of ignition.
- Use in well-ventilated areas.
- For more information see the safety data sheet.