

SA 008

1. Description:

SA-008 is an splice adhesive, designed for bonding giscolene EPDM membranes.

2. Characteristics

- Excellent ageing resistance.
- Excellent adherence.
- Good resistance to heat and cold.

3. Installation

Stir the adhesive before and during use. Restore the adhesive to room temperature prior to use, if exposed to lower than 10°C temperatures.

Apply in a thick, even, smooth coat on both surfaces simultaneously with a 75 to 100 mm wide solvent resistant paint brush. Do not use circular motions for applying splice adhesive (no paint rollers), allow the adhesive to flash off. In cold weather, moisture contamination of the adhesive can occur when condensation/frost forms on the adhesive while the solvents flash off. For further informations please contact us.

4. Coverage

For 100 mm wide joint, about 9 lineal meters can be made with 1 litre (about 14 lineal meters for 75 mm wide joints). Thin application will dry quickly, whereas thick will dry slowly. A uniform application is required to avoid mixed results. Thinning of the adhesive is not allowed.

5. Properties

Base	synthetic polymer
Colour	Black
Solvents	Organic
Dry residue (%)	41 ± 2
Density at 20°C	0,88
Viscosity (mPa.s)	2500 ± 500

6. Packaging/Storage/Shelf life

Packaging: 1 and 5 litres/can

Storage: Store in original, unopened cans at temperatures between 15°C and 25°C. Keep the material out of direct sunlight until ready for application.

Shelf life: 12 months if stored in original container if maintained at temperatures between 15°C and 25°C. Once opened, use the adhesive within 48 hours.

7. Precautions

- Flammable.
- Keep away from sources of ignition.
- Do not smoke when using.
- Store and use the material in well ventilated areas.
- May cause sensibility by inhalation.
- Refer to the Material Safety Data Sheet